



## SANODAL® TURQUOISE PLW LIQUID

***Sanodal Turquoise PLW*** is recommended for all applications ranging from exterior architectural panels and extrusions, stadium seating, and highway signs to such small objects as costume jewelry, nameplates and foil labels.

### **PROPERTIES:**

Description:	Phthalocyanine dye (liquid concentrate)
Light fastness:	8 + (architectural quality)
Weather fastness:	Excellent

### **RECOMMENDED APPLICATION DETAILS:**

Concentration:	0.5 - 5.0 g/l
pH range:	5.0 - 6.0
Buffering:	Anodal® Dye Buffer Liquid (required)
Temperature:	140° - 160° F.
Immersion Time:	2 - 20 min

For architectural quality finishes, please refer to the processing requirements as described in the Reliant bulletin, the *Sanodal System*.

### **PREFERRED SEALING METHODS:**

Hot:	Anodal ASL or Anodal AS
Medium:	Anodal MS-1 New or Anodal MTS Plus
Cold:	Anodal CS-2, Anodal CS-2N or Anodal CS3

### **PRECAUTIONS:**

This dye is contaminated with aluminum, copper and iron salts as well as sulfates. Effective rinsing and care to eliminate drag-in are required.

### **ENVIRONMENTAL CONSIDERATIONS:**

This RoHS compliant product contains copper as an integral part of the dye. The preferred method of disposal is described in the Reliant bulletin, the *Anodal WT System*.

Recommendations, notices or instructions as to handling, use, storage or disposal of this product, including its use alone or in combination with other products, or as to any apparatus or process for its use are based upon information believed to be reliable. No liability is taken with respect to any such recommendations or instructions. Sole and exclusive warranty is that products comply with published chemical and physical specifications as provided on the certificate of analysis. No other warranties, either express or implied are given.