



SANODYE® PINK TEJ pdr.

Sanodye Pink TEJ produces shades ranging from pale to deep pink depending upon concentration and coating thickness. This dye outperforms other products in its ability to produce light level shades of pink.

PROPERTIES:

Chemical description: Azo dye (powder)
Heat fastness: Good up to 250° F.

RECOMMENDED APPLICATION DETAILS:

Concentration: 0.5 - 5 g/l
pH range: 5.5 - 6.0
Buffering: Anodal® Dye Buffer Liquid
Temperature: 140° - 160° F.
Immersion time: 2 - 20 minutes

PREFERRED SEALING METHODS:

Hot: Anodal ASL or Anodal AS
Medium: Anodal MS-1 New or Anodal MTS Plus
Cold: Anodal CS-2, Anodal CS-2N or Anodal CS3

PRECAUTIONS:

The color value of the dye solution is affected by contamination with aluminum and other metal salts. Effective rinsing and care to eliminate drag-in are suggested for maximum tank life.

ENVIRONMENTAL CONSIDERATIONS:

This is a RoHS compliant product that contains no heavy metals.

Recommendations, notices or instructions as to handling, use, storage or disposal of this product, including its use alone or in combination with other products, or as to any apparatus or process for its use are based upon information believed to be reliable. No liability is taken with respect to any such recommendations or instructions. Sole and exclusive warranty is that products comply with published chemical and physical specifications as provided on the certificate of analysis. No other warranties, either express or implied are given.