



SANODYE® YELLOW 3GL

Sanodye Yellow 3GL is recommended for interior as well as exterior architectural applications. The color produced is an attractive fluorescent-like yellow with a slight green cast.

PROPERTIES:

Chemical Description:	Quinoline dye (granular)
Light fastness:	Architectural (8+)
Weather fastness:	Excellent
Heat fastness:	Moderate up to 400° F.

RECOMMENDED APPLICATION DETAILS:

Concentration:	0.5 – 5.0 g/l
pH range:	5.0 – 6.0
Buffering	Anodal® Dye Buffer Liq. (not required)
Temperature:	140 –160° F.
Immersion time:	2 - 20 min.

For architectural quality finishes, please refer to the processing requirements as described in the Reliant bulletin, the *Sanodal System*.

PREFERRED SEALING METHODS:

Hot:	Anodal ASL or Anodal AS
Medium:	Anodal MS-1 New or Anodal MTS Plus
Cold:	Anodal CS-2, Anodal CS-2N or Anodal CS3

PRECAUTIONS:

The color value of the dye solution is affected by contamination with aluminum and other metal salts and especially, sulfates. Effective rinsing is an absolute necessity. Sealing solutions must be free of sulfates and phosphates to prevent color loss. Some loss of color may occur on sealing.

ENVIRONMENTAL CONSIDERATIONS:

This is a RoHS compliant product that contains no heavy metals.

Recommendations, notices or instructions as to handling, use, storage or disposal of this product, including its use alone or in combination with other products, or as to any apparatus or process for its use are based upon information believed to be reliable. No liability is taken with respect to any such recommendations or instructions. Sole and exclusive warranty is that products comply with published chemical and physical specifications as provided on the certificate of analysis. No other warranties, either express or implied are given.