



## SANODURE® BRONZE 2LW

**Sanodure Bronze 2LW** is widely used for bronze shades. On thicker anodic coatings and at higher concentrations it will produce an attractive, deep reddish brown. In combination with Sanodure Grey NL Liquid it may be used to match electrolytic bronze shades used on out-door architectural elements.

Chemical description:	Azo dye (granular)
Light fastness:	7 (very good)
Heat fastness:	Moderate up to 250 ° F

### **RECOMMENDED APPLICATION DETAILS:**

Concentration:	0.5 - 5.0 g/l
pH range:	5.5 - 6.0
Buffering:	Anodal® Dye Buffer Liquid
Temperature:	80° - 120° F.
Immersion time:	2 - 10 minutes

### **PREFERRED SEALING METHODS:**

Hot:	Anodal ASL or Anodal AS
Medium:	Anodal MS-1 New or Anodal MTS Plus
Cold:	Anodal CS-2, Anodal CS-2N or Anodal CS3

### **PRECAUTIONS:**

This dye solution is sensitive to drag-in, therefore, effective rinsing is strongly advised. Maximum tank life is obtained by operation at low temperature and high concentration.

### **ENVIRONMENTAL CONSIDERATIONS:**

This RoHS compliant product contains chromium as an integral part of the dye. The preferred method of disposal is described in the Reliant bulletin, the *Anodal WT System*.

Recommendations, notices or instructions as to handling, use, storage or disposal of this product, including its use alone or in combination with other products, or as to any apparatus or process for its use are based upon information believed to be reliable. No liability is taken with respect to any such recommendations or instructions. Sole and exclusive warranty is that products comply with published chemical and physical specifications as provided on the certificate of analysis. No other warranties, either express or implied are given.