

SANODYE® PINK BLS

Sanodye Pink BLS produces shades ranging from pale to deep pink depending upon concentration and coating thickness.

PROPERTIES:

Chemical description: Azo dye (powder

Form: Powder

RECOMMENDED APPLICATION DETAILS:

Concentration: 0.5 - 5 g/l pH range: 5.5 - 6.0

Buffering: Anodal® Dye Buffer Liquid

Temperature: 140° - 160° F. Immersion time: 2 - 20 minutes

PREFERRED SEALING METHODS:

Hot: Anodal ASL or Anodal AS

Medium: Anodal MS-1 New or Anodal MTS Plus Cold: Anodal CS-2, Anodal CS-2N or Anodal CS3

PRECAUTIONS:

Notable color loss can be expected as sulfate levels climb. Effective rinsing and care to eliminate drag-in are suggested for maximum tank life. Color loss can also be expected when pH is operated higher than the recommended value. Good agitation may be required to achieve level color.

ENVIRONMENTAL CONSIDERATIONS:

This is a RoHS compliant product that contains no heavy metals.

Recommendations, notices or instructions as to handling, use, storage or disposal of this product, including its use alone or in combination with other products, or as to any apparatus or process for its use are based upon information believed to be reliable. No liability is taken with respect to any such recommendations or instructions. Sole and exclusive warranty is that products comply with published chemical and physical specifications as provided on the certificate of analysis. No other warranties, either express or implied are given.

Page 1 of 1 Revised June 2, 2015
RELIANT ALUMINUM PRODUCTS. LLC RELIANTALUMINUMPRODUCTS.COM