



## SANODAL® BLACK 2LW

**Sanodal Black 2LW** produces a blue black color which may be shaded with *Sanodure Orange RL* to obtain a jet black. At lower concentrations it is used for blue grey and midnight blue shades.

Chemical description:	Azo dye (granular)
Light fastness:	8+ (architectural)
Weather fastness:	Excellent
Heat fastness:	Moderate up to 250° F.

### **RECOMMENDED APPLICATION DETAILS:**

Concentration:	10-20 g/l (for black)
pH range:	4.2 - 4.8
Buffering:	Anodal® Dye Buffer Liquid (not required)
Temperature:	120° - 140° F.
Immersion time:	10 - 30 minutes (for black)

For architectural quality finishes, please refer to the processing requirements as described in the Reliant bulletin, the *Sanodal System*.

### **PREFERRED SEALING METHODS:**

Hot:	Anodal ASL or Anodal AS
Medium:	Anodal MS-1 New or Anodal MTS Plus
Cold:	Anodal CS-2, Anodal CS-2N or Anodal CS3

### **PRECAUTIONS:**

The color value of the dye solution is affected by contamination with aluminum and other metal salts. Effective rinsing and care to eliminate drag-in are required to obtain maximum tank life.

### **ENVIRONMENTAL CONSIDERATIONS:**

This RoHS compliant product contains chromium as an integral part of the dye. The preferred method of disposal is described in the Reliant bulletin, the *Anodal WT System*.

Recommendations, notices or instructions as to handling, use, storage or disposal of this product, including its use alone or in combination with other products, or as to any apparatus or process for its use are based upon information believed to be reliable. No liability is taken with respect to any such recommendations or instructions. Sole and exclusive warranty is that products comply with published chemical and physical specifications as provided on the certificate of analysis. No other warranties, either express or implied are given.