



SANODURE® FAST GOLD L

Sanodure Fast Gold L is handy for production of brass and yellow-gold shades where high fade resistance is required. It forms a synergistic combination with *Sanodure Fast Bronze L* for matching the complete range of gold alloys.

Chemical description:	Azo dye (granular)
Light fastness:	7 – 8 (very good)
Heat fastness:	Moderate up to 400 ° F.

RECOMMENDED APPLICATION DETAILS:

Concentration:	0.5 - 5.0 g/l
pH range:	5.0 - 6.0
Buffering:	Anodal® Dye Buffer Liquid
Temperature:	120 - 140 ° F.
Immersion time:	2 - 20 min. for normal applications

PREFERRED SEALING METHODS:

Hot:	Anodal ASL or Anodal AS
Medium:	Anodal MS-1 New or Anodal MTS Plus
Cold:	Anodal CS-2, Anodal CS-2N or Anodal CS3

PRECAUTIONS:

Contamination of the sealing solution with traces of phosphates and/or silicates will cause excessive color loss. This can be overcome to some degree by dyeing at higher temperatures.

ENVIRONMENTAL CONSIDERATIONS:

This RoHS compliant product contains copper as an integral part of the dye. The preferred method of disposal is described in the Reliant bulletin, the *Anodal WT System*.

Recommendations, notices or instructions as to handling, use, storage or disposal of this product, including its use alone or in combination with other products, or as to any apparatus or process for its use are based upon information believed to be reliable. No liability is taken with respect to any such recommendations or instructions. Sole and exclusive warranty is that products comply with published chemical and physical specifications as provided on the certificate of analysis. No other warranties, either express or implied are given.