



SANODURE® YELLOW BROWN 2G

Sanodure Yellow Brown 2G yields an interesting range of brown shades the primary use of which is for decorative trim.

Chemical description:	Azo dye blend (granular)
Light fastness:	Good (6 – 7)
Heat fastness:	Good at 250° F.

RECOMMENDED APPLICATION DETAILS:

Concentration:	0.5 - 5.0 g/l
pH range:	5.0 – 6.0
Buffering:	Anodal® Dye Buffer Liquid
Temperature:	140° - 160° F.
Immersion time:	2 - 20 minutes

PREFERRED SEALING METHODS:

Hot:	Anodal ASL or Anodal AS
Medium:	Anodal MS-1 New or Anodal MTS Plus
Cold:	Anodal CS-2, Anodal CS-2N or Anodal CS3

PRECAUTIONS:

The dye solution is adversely affected by contamination with aluminum and other metal salts as well as sulfates. Effective rinsing and care to eliminate drag-in are required.

ENVIRONMENTAL CONSIDERATIONS:

This RoHS compliant product contains chromium as an integral part of the dye. The preferred method of disposal is described in the Reliant bulletin, the *Anodal WT System*.

Recommendations, notices or instructions as to handling, use, storage or disposal of this product, including its use alone or in combination with other products, or as to any apparatus or process for its use are based upon information believed to be reliable. No liability is taken with respect to any such recommendations or instructions. Sole and exclusive warranty is that products comply with published chemical and physical specifications as provided on the certificate of analysis. No other warranties, either express or implied are given.